

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
8 July 2004 (08.07.2004)

PCT

(10) International Publication Number
WO 2004/056886 A1

(51) International Patent Classification⁷: **C08F 30/02**,
2/38, 20/04

[GB/GB]; 57 Gorseway, Whoberley, Coventry CV5 8BL
(GB).

(21) International Application Number:
PCT/GB2003/005570

(74) Agent: **BARKER BRETTELL**; 138 Hagley Road, Edg-
baston, Birmingham B16 9PW (GB).

(22) International Filing Date:
19 December 2003 (19.12.2003)

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR,
CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD,
GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR,
KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN,
MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU,
SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0229684.6 20 December 2002 (20.12.2002) GB

(84) Designated States (*regional*): ARIPO patent (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **RHODIA
CONSUMER SPECIALTIES LIMITED** [GB/GB]; Oak
House, Reeds Crescent, Hertfordshire WD24 4QP (GB).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **WOODWARD**,
Gary [GB/GB]; 6 Kelstern Close, Northwich, Cheshire
CW9 5QR (GB). **OTTER, Graham, Philip** [GB/GB];
4 Bracken Grove, Catshill, Bromsgrove, Worcestershire
B61 0PB (GB). **DAVIS, Keith, Philip** [GB/GB]; 3 Holly
Close, Kinver, Staffordshire DY7 6BP (GB). **HUAN, Kim**

Published:

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: BIODEGRADABLE POLYMERS

(57) Abstract: A phosphorus-containing polymer is provided comprising the reaction product of a chain-transfer agent having at least one pH bond with an unsaturated carboxylic, phosphonic or sulphonic acid. The invention also provides the aforementioned phosphorus-containing polymer further comprising phosphorus-containing end-caps. The polymers have a biodegradability of at least 20% per 28 days (as determined by OECD 306).

WO 2004/056886 A1

1 JC20 Rec'd PCT/PTO 20 JUN 2005

BIODEGRADABLE POLYMERS

This invention relates to biodegradable polymers, especially phosphorus-containing polymers which meet or exceed the minimum statutory requirements for biodegradability. This invention also relates to a method of making such polymers and to their use as scale-inhibitors in oilfield applications.

There is a need for more environmentally benign chemicals to be used in the extraction of petroleum from subsea reservoirs, such as those located in the North Sea. Chemicals that may ultimately be discharged to the marine environment must have low toxicity towards marine organisms and should not exhibit a tendency to build up in their tissues (bio-accumulate). It is also desirable that a product does not accumulate in the environment, but can be degraded chemically or by the action of micro-organisms (biodegradation). Thus, the authorities who regulate the use of chemicals in the North Sea stipulate a threshold of at least 20% biodegradation in 28 days (OECD 306) as part of the "pre-screening" test for the 'CHARM' model, which is currently used to assess environmental impact.

Polymers having phosphorus-containing end-caps, especially polymers comprising acrylic acid, are widely used as scale-inhibitors, particularly in oilfield applications. Examples of such polymers are disclosed in the applicant's EP-A-0 861 846, the contents of which are incorporated herein by reference.

It is known that the biodegradability of acrylic acid-containing polymers, which are generally poorly biodegraded, is greatly improved by reducing the weight average molecular weight (Mw) below 700 Daltons. See, for example, J.Environ.Polym.Degrad., 1997, 5, p41-48. It was suggested that one possible means of producing polymers with Mw in this region

might be afforded by the use of the lower oxo acids of phosphorus (III) and their salts as chain-transfer agents, but it was by no means certain that the resulting polymers would be as biodegradable as the corresponding phosphorus-free polyacrylates. Such polymers are being
5 increasingly utilised as scale inhibitors during the secondary recovery of oil from reservoirs with very demanding water chemistry and conditions, so it is important that low molecular weight modifications retain this functionality. The effect of reducing molecular weight on scale inhibitor performance is again not predictable: for simple polycarboxylates there
10 is often an optimum range of molecular weight, either side of which performance often falls off markedly.

The present invention provides, in a first aspect, a phosphorus-containing polymer comprising the reaction product of an unsaturated phosphonic
15 acid with a chain-transfer agent, the polymer having improved biodegradability as compared to the same polymer when made in the absence of the chain-transfer agent.

Preferably, the polymer has a biodegradability of at least 20% per
20 28 days (as determined by OECD 306).

The chain-transfer agent may be, for example,

- (a) benzene, toluene, ethylbenzene or chlorobenzene;
- (b) methylene chloride, ethylene chloride, chloroform or carbon
25 tetrachloride;
- (c) acetone, thiophenol, n-butyl thiol or dodecyl thiol.

We have found that by the use of chain-transfer agents containing at least one 'P-H' bond, it is possible to produce polymers which combine
30 excellent activity as oilfield scale inhibitors with good biodegradability, often in excess of that required by 'OECD 306'.

In a first preferred embodiment of the first aspect of the present invention, there is provided a phosphorus-containing polymer comprising the reaction product of a chain-transfer agent having at least one P-H
5 bond with an unsaturated carboxylic, phosphonic or sulphonic acid, the polymer having a biodegradability of at least 20% per 28 days (as determined by OECD 306).

We have also found that polymers which include phosphorus-containing
10 end-caps can have a desirably high biodegradability as well as being effective as oilfield scale inhibitors.

Thus, in a second preferred embodiment of the first aspect of the present invention, there is provided a polymer having phosphorus-containing end-
15 caps and comprising the reaction product of a chain-transfer agent having at least one P-H bond with an unsaturated carboxylic, phosphonic or sulphonic acid, said polymer having a biodegradability of at least 20% per 28 days (as determined by OECD 306).

20 Preferably, the chain-transfer agent having at least one P-H bond is hypophosphorous acid or a water-soluble salt (such as an alkali metal salt or ammonium salt) of said acid.

Preferably, the unsaturated carboxylic acid is acrylic acid or a water-
25 soluble salt of said acid.

Alternatively, the unsaturated carboxylic acid may be, for example, methacrylic acid, maleic acid, fumaric acid, itaconic acid, aconitic acid, citraconic acid, mesaconic acid, crotonic acid, isocrotonic acid, angelic
30 acid or tiglic acid (or a water-soluble salt of any of said acids).

Suitably, the unsaturated phosphonic acid is vinylphosphonic acid (VPA) or vinylidene-1,1-diphosphonic acid (VDPA) or a water-soluble salt of either of said acids.

- 5 Preferably, the unsaturated sulphonic acid is vinylsulphonic acid (VSA) or a water-soluble salt of said acid.

In a third preferred embodiment of the first aspect of the present invention, the polymer comprises a telomer which is the reaction product
10 of an adduct of vinylphosphonic acid and hypophosphorous acid (hereinafter referred to as "PPE-endcapper") with acrylic acid, said telomer being hereinafter referred to as a "PPE-endcapped polyacrylate".

The ratio of the PPE-endcapper to acrylic acid is suitably in the range 1:5
15 to 1:20 molar and preferably about 1:10 molar.

Preferably, the polymers according to the present invention exhibit a weight average molecular weight such that at least 20% by weight of the polymer has a weight average molecular weight of 1000 or lower. More
20 preferably, at least 35% by weight of the polymer has a weight average molecular weight of 1000 or lower.

In a second aspect, the present invention provides a method of making a polymer according to the first aspect of the present invention, in which
25 the chain-transfer agent and the unsaturated acid are reacted together in the presence of a free-radical initiator.

The free-radical initiator is preferably an alkali metal persulphate (especially sodium persulphate).

Alternatively, the free-radical initiator may be an alkali metal peracetate, hydrogen peroxide, a hydroperoxide, chlorine dioxide, an alkali metal chlorate or hypochlorite, an organometallic hydride, an azo-compound (e.g. 4,4'-azo-bis-cyanovaleric acid), electrolysis, ultraviolet or other
5 ionising radiation, ultrasound, or any combination of the foregoing.

The present invention provides, in a third aspect, a polymer made by the method disclosed in the three immediately-preceding paragraphs.

10 In a fourth aspect, the present invention provides the use, as a scale-inhibitor for oilfield applications, of a polymer according to the first or third aspects of the present invention.

Preferred embodiments of the present invention will be illustrated by way
15 of the following Examples.

Example 1

A PPE-endcapped polyacrylate (Ref. KH59, ratio of PPP-endcapper to
20 acrylic acid 1:10 molar) was prepared as follows:

The reagents shown in TABLE A (below) were taken

TABLE A

Reagent	Quantity (g)	Dilution (ml water)	Formula Weight	Quantity (moles)
Acrylic acid (99%)	144	486	72	1.98
Sodium hydroxide (46-48%)	60	-	40	0.71
*PPE-endcapper (17.2%)	280	-	240	0.20
Sodium persulphate	23.8	177.4	238	0.10

*The endcapper consisted essentially of trisodium 1-phosphono-2-phosphino ethane, prepared according to the disclosure in the applicants' EP-A-0 861 846.

Half of the PPE endcapper (140 g, 0.1 mol) was charged to a 1-litre jacketed reactor, stirred and heated to 95°C.

Meanwhile, three feeds were prepared:

Feed (1) An initiator solution of sodium persulphate (23.8 g, 0.1 mol) and water (177.4 g);

Feed (2) Acrylic acid (144 g, 1.99 mol) was diluted with ice (200 g) and water (286 g). The pH was adjusted to 4 by addition of the sodium hydroxide solution (60 g of 46-48% solids, 0.71 mol). Half of this total solution ($690 \text{ g} \times \frac{1}{2} = 345 \text{ g}$) was added to the other half of the PPE endcapper (140 g, 0.10 mol) to give 485 g of Feed 2;

Feed (3) The remaining acrylate solution (345 g).

Once the reaction temperature had been reached, Feeds 1 and 2 were simultaneously started by means of separate peristaltic pumps. Feed 1 was

added over 8 hours and Feed 2 was added in at a steady rate over 4 hours. On completion of Feed 2, Feed 3 was added over 3½ hours. Therefore, the initiator Feed (1) runs for ½ hour longer than Feed 3. When all feeds had finished, the reaction was kept at reflux for a further ½ hour, then
5 allowed to cool (total reaction time = 8½ hours).

At this stage the product was at a concentration of 16.3% w/w actives. To achieve the desired concentration of 25% w/w actives (32.6% w/w solids), water (403 g) was removed by rotary evaporation.
10 (Concentrations based on 100% yield).

Example 2

Another PPE-endcapped polyacrylate (Ref. KH70, ratio of PPE endcapper
15 to acrylic acid 1:10 molar) was prepared by the method of Example 1 (above), except that in the preparation of Feed 2, the acrylic acid was fully neutralised with the sodium hydroxide solution, so that the reaction was carried out at pH7 instead of pH4.

20 Performance and Biodegradability Tests

The products of Example 1 and Example 2 (above), together with two comparative products, were subjected to the Tube Block Test described in our published application WO 01/57050, Example 3, and to the
25 Biodegradability Test (OECD 306). The results are set out in TABLE B (below). In each case, a PPE-endcapped polyacrylate in which the PPE endcapper was trisodium 1-phosphono-2-phosphino-ethane was used.

TABLE B

Product	PPE to Acrylic acid ratio (molar)	Weight Average Molecular Weight (g/ml)	% Product with Mw below 100	Tube Block test (ppm active acid)	Bio-degradability (%per 28 days)
Comparative A (B13L1)	1:20	3994	18	120,120,120	15
Comparative B (KH71)	1:15	2680	25	100,100,120	5
Example 1 (KH59)	1:10	2598	42	120,120,120	23
Example 2 (KH70)	1:10	2116	31	100,120,120	28

- 5 It will be seen that the products of Examples 1 and 2 of the present invention each satisfied the conditions of OECD 306.

CLAIMS

1. A phosphorus-containing polymer, comprising the reaction product of an unsaturated phosphonic acid with a chain-transfer agent, the polymer having improved biodegradability as compared to the same polymer when made in the absence of the chain-transfer agent.
2. A polymer according to Claim 1, the polymer having a biodegradability of at least 20% per 28 days (as determined by OECD 306).
3. A polymer according to Claim 1, in which the chain-transfer agent is benzene, toluene, ethylbenzene or chlorobenzene.
4. A polymer according to Claim 1, in which the chain-transfer agent is methylene chloride, ethylene chloride, chloroform or carbon tetrachloride.
5. A polymer according to Claim 1, in which the chain-transfer agent is acetone, thiophenol, n-butyl thiol or dodecyl thiol.
6. A phosphorus-containing polymer comprising the reaction product of a chain-transfer agent having at least one P-H bond with an unsaturated carboxylic, phosphonic or sulphonic acid, the polymer having a biodegradability of at least 20% per 28 days (as determined by OECD 306).
7. A polymer according to Claim 6, having phosphorus-containing end-caps and comprising the reaction product of a chain-transfer agent having at least one P-H bond with an unsaturated carboxylic, phosphonic

or sulphonic acid, said polymer having a biodegradability of at least 20% per 28 days (as determined by OECD 306).

8. A polymer according to Claim 6 or 7, in which the chain-transfer agent having at least one P-H bond is hypophosphorous acid or a water-soluble salt of said acid.

9. A polymer according to Claim 8, in which the chain-transfer agent is an alkali metal salt or an ammonium salt of hypophosphorous acid.

10. A polymer according to any one of Claims 6 to 9, in which the unsaturated carboxylic acid is acrylic acid or a water-soluble salt of said acid.

11. A polymer according to any one of Claims 6 to 9, in which the unsaturated carboxylic acid is methacrylic acid, maleic acid, fumaric acid, itaconic acid, aconitic acid, citraconic acid, mesaconic acid, crotonic acid, isocrotonic acid, angelic acid, tiglic acid or a water-soluble salt of any of said acids.

12. A polymer according to Claim 1 or to any one of Claims 6 to 9, in which the unsaturated phosphonic acid is vinylphosphonic acid (VPA), vinylidene-1,1-diphosphonic acid (VDPA) or a water-soluble salt of either of said acids.

13. A polymer according to any one of Claims 6 to 9, in which the unsaturated sulphonic acid is vinylsulphonic acid (VSA) or a water-soluble salt of said acid.

14. A polymer according to any one of Claims 1 to 10, comprising a telomer which is the reaction product of a PPE-endcapper (as hereinbefore defined) with acrylic acid.
- 5 15. A polymer according to Claim 14, in which the ratio of the PPE-endcapper to acrylic acid is in the range 1:5 to 1:20 molar.
16. A polymer according to Claim 14 or 15, in which the ratio of the PPE-endcapper to acrylic acid is about 1:10 molar.
- 10 17. A polymer according to any one of Claims 1 to 16, in which at least 20% by weight of the polymer has a weight average molecular weight of 1000 or lower.
- 15 18. A polymer according to Claim 17, in which at least 35% by weight of the polymer has a weight average molecular weight of 1000 or lower.
19. A method of making a polymer according to any one of Claims 1 to 18, in which the chain-transfer agent and the unsaturated acid are
20 reacted together in the presence of a free-radical initiator.
20. A method according to Claim 19, in which the free-radical initiator is an alkali metal persulphate.
- 25 21. A method according to Claim 20, in which the free-radical initiator is sodium persulphate.
22. A method according to Claim 19, in which the free-radical initiator is an alkali metal peracetate, hydrogen peroxide, a hydroperoxide,
30 chlorine dioxide, an alkali metal chlorate or hypochlorite, an

organometallic hydride, an azo-compound or any two or more of the foregoing.

23. A method according to Claim 22, in which the free-radical initiator
5 is 4,4'-azo-bis-cyanovaleric acid.

24. A method according to Claim 19, in which the free-radical initiator
comprises electrolysis, ultraviolet or other ionising radiation, ultrasound
or any two or more of the foregoing.

10

25. A method of making a biodegradable polymer, substantially as
hereinbefore described with reference to the Examples.

26. A phosphorus-containing polymer comprising the reaction product
15 of a chain transfer agent with an unsaturated carboxylic, phosphonic or
sulphonic acid, the polymer having improved biodegradability as
compared to the same polymer when made in the absence of the chain-
transfer agent.

20 27. A phosphorus-containing polymer as claimed in Claim 25 having
phosphorus-containing end caps.

28. A biodegradable polymer as claimed in Claims 1 to 18, 26 and 27
made by the method of any one of Claims 19 to 25.

25

29. The use of a biodegradable polymer according to any one of
Claims 1 to 18, 26 and 27 as a scale-inhibitor for oilfield applications.

INTERNATIONAL SEARCH REPORT

PCT/GB 03/05570

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 C08F30/02 C08F2/38 C08F20/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 861 846 A (ALBRIGHT & WILSON UK LTD) 2 September 1998 (1998-09-02) cited in the application	
A	EP 0 405 818 A (ROHM AND HAAS CO.) 2 January 1991 (1991-01-02)	

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

15 April 2004

Date of mailing of the international search report

23/04/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Cauwenberg, C

INTERNATIONAL SEARCH REPORT

PCT/GB 03/05570

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0861846	A	02-09-1998	AT 236175 T	15-04-2003
			AU 727273 B2	07-12-2000
			AU 5627498 A	03-09-1998
			CA 2230517 A1	26-08-1998
			DE 69812753 D1	08-05-2003
			DE 69812753 T2	05-02-2004
			DK 861846 T3	21-07-2003
			EP 0861846 A2	02-09-1998
			ES 2196413 T3	16-12-2003
			GB 2322627 A ,B	02-09-1998
			NO 980782 A	27-08-1998
			US 6071434 A	06-06-2000
EP 0405818	A	02-01-1991	US 5077361 A	31-12-1991
			AT 136910 T	15-05-1996
			BR 9003066 A	27-08-1991
			CA 2018772 A1	26-12-1990
			DE 69026539 D1	23-05-1996
			DE 69026539 T2	02-10-1996
			DK 405818 T3	13-05-1996
			EP 0405818 A2	02-01-1991
			ES 2086372 T3	01-07-1996
			IE 902291 A1	16-01-1991
			JP 2723345 B2	09-03-1998
			JP 3121101 A	23-05-1991
			MX 171617 B	09-11-1993
			PT 94477 A	08-02-1991
			US 5216099 A	01-06-1993
			ZA 9004777 A	27-03-1991